

## U SeaProtect Wired Mat



### Wired Mats unfaced – density from 36 to 66 kg/m<sup>3</sup>

unique high-performance profile: It combines safety, comfort and ease of handling.



#### **FIRE RESISTANCE.**

ULTIMATE provides effective fire resistance, but also very good performance in reaction to fire.



#### **THERMAL INSULATION.**

Excellent thermal insulation combined with unique efficiency.



#### **SOUND ABSORPTION.**

Improved acoustic comfort due to its excellent sound absorption and sound insulation properties.



#### **LIGHTWEIGHT.**

Increase insulation – reduce weight. ULTIMATE combines high fire & thermal performance with very low weight.

# U SeaProtect Wired Mat



CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES							STANDARD
Thermal conductivity	T	[°C]	10	50	100	150	200	300	400	EN 12667
U SeaProtect Wired Mat 36	λ	[W/(m·K)]	0.032	0.037	0.045	0.055	0.069	0.104	0.153	
U SeaProtect Wired Mat 48				0.036	0.042	0.051	0.060	0.086	0.122	
U SeaProtect Wired Mat 66				0.031	0.035	0.040	0.047	0.054	0.072	
Thermal behaviour	T	[°C]	Exposure temperature up to 650°C is possible (depending on density). Above 150°C the glue begins to volatilize.							AGI Q 132

CHARACTERISTIC	SYMBOL	UNIT	THICKNESS	VALUES	STANDARD
Acoustic absorption value	α <sub>w</sub>	-	U SeaProtect Wired Mat 48 100 mm	1.00	-
			U SeaProtect Wired Mat 66 50 mm		

CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES	VALUES	STANDARD
Resistivity to air flow	σ	[KPa.s/m²]	U SeaProtect Wired Mat 36	30	DIN EN 29053
			U SeaProtect Wired Mat 66	60	

CHARACTERISTIC	SYMBOL	UNIT	QUANTITIES AND DECLARED VALUES	STANDARD
Specific thermal capacity	c	kJ/(kg·K)	0.84	ISO 10456
Reaction to fire	-	-	Melting point according to DIN 4102, part 17: ≥ 1000 °C. Non combustible according to IMO-Resolution. Homologated for shipbuilding according to EC Type Examination. Certificates Nr.: MED-B+D Certificate = visit our website.	DIN 4102 IMO
Chemical behaviour	-	-	Sulphide free.	-
Application field	-	-	Thermal insulation, acoustic insulation and fire protection constructions in shipbuilding.	-
Material	-	-	Mineral wool with quality marks EUCER and RAL by the Gütegemeinschaft Mineralwolle e. V., unrisky regarding health according to German decree on dangerous substances, decree on prohibition of chemicals and to regulation EC No 1272/2008 Note Q.	-
Water vapour diffusion resistance factor	μ	-	- 1.00	ISO 10456
Quality management	-	-	ISOVER is certified according to EN ISO 9001 and EN ISO 14001.	DIN EN ISO 9001 DIN EN ISO 14001

DELIVERY FORM: STANDARD DIMENSIONS / PACKAGING INFORMATION*					
Products	Thickness d (mm)	Length l (m)	Width b (m)	m²/pack	m²/pallet
U SeaProtect Wired Mat 48	100	3.10	0.60	3.72	66.96
U SeaProtect Wired Mat 66	50	6.00	0.60	7.20	129.60

\* On some products, a minimum order quantity is required. Other dimensions on request.



## www.isover.es

This data sheet was completed on the date indicated on the right-hand side and was done with ISOVER's knowledge and experience at that time. However, it does not offer any legal guarantee, unless it has been expressly agreed. Bearing in mind that our knowledge and developments of building solutions and products are continuously evolving, ensure that when you use this data sheet, it is the latest version. The description of the product applications does not take into account the special circumstances that may arise for a specific case. Please check that this product is the appropriate one for the application you are considering. For more detailed information, contact our network of ISOVER branches.

SAINT-GOBAIN ISOVER IBÉRICA, S.L. • C/ Príncipe de Vergara, 132 • 28002 Madrid • Spain

SEP-2024

