



Drywall 37

Partition walls

Description

Semi-rigid panels and rolls of **arena** mineral wool ISOVER, non-hydrophilic, unfaced.

Applications

Due to excellent thermal and acoustic properties, **Drywall 37** mineral wool products range of ISOVER is the best choice for:

- Partition walls, particularly drywall with metal stud.

CTE stack Technical properties

Symbol	Parameter	Icon	Units	Value	Norm
λ_D	Stated thermal conductivity		mW/m.K	0.037	EN 12667 EN 12939
C_p	Approximate specific heat		J/(Kg.K)	800	-
AF_R	Resistance to air flow		kPa.s/m ²	> 5	EN 29053
-	Reaction to fire		Euroclase	A1	EN 13501-1
WS	Water absorption		kg/m ²	< 1	EN 1609
MU	Resistance to water vapour diffusion factor, μ		-	1	EN 12086
DS	Dimensional stability, $\Delta\epsilon$		%	< 1	EN 1604

Thickness d, mm	Stated thermal resistance R_D , m ² .K/W	Acoustic absorption coefficient AW , α_w	Designation code
EN 823	EN 12667 EN 12939	EN ISO 354	EN 13162
50	1.35	0.70	MW-EN 13162-T3-DS(23,90)-WS-MU1-AW0,70-AFr5
60	1.60	0.80	MW-EN 13162-T3-DS(23,90)-WS-MU1-AW0,80-AFr5
75	2.00		

Presentation



	Thickness d (mm)	Length l (m)	Width b (m)	m ² /pack	m ² /pallet	m ² /truck
Panel	50	1.35	0.40	12.96	233.28	4199
	50	1.35	0.60	19.44	311.04	5599
	60	1.35	0.40	10.80	194.40	3499
	60	1.35	0.60	16.20	259.20	4666
	75	1.35	0.40	8.64	155.52	2799
	75	1.35	0.60	12.96	207.36	3732
Roll	50	12.15	0.40	14.58	291.60	5249
	50	12.15	0.60	14.58	291.60	5249
	60	10.80	0.40	12.96	259.20	4666
	60	10.80	0.60	12.96	259.20	4666

Advantages

- Optimum thermal and acoustic insulation of both vertical and horizontal interior partitions.
- Suitable for new and renovation works.
- Flexible material. Easy to install product around windows, rafters, pillars, etc. Keeping its continuity and initial state.
- Sustainable product with a composition of more than 50% recycled material. 100% recyclable material.
- Inert material, inhospitable for micro-organisms.
- Maintains system performance throughout the useful life of the building, it does not degrade over time.



Certificates



Installation guide

Additional information available at: www.isover.es



Saint Gobain Isover Iberica, S.L. reserves the right to totally or partially change the information in this document without prior notification. The company cannot guarantee the absence of inadvertent errors.